

Fosroc Renderoc FC

Single component polymer modified cementitious pinhole filler

Uses

Renderoc FC is designed for application to minor imperfections in concrete and masonry surfaces. It is suitable for application in the range of feather edge to 3 mm, and can be used in the following situations:

- Filling pinholes prior to over-coating
- General re-profiling over large areas, up to 3 mm depth
- Fairing coat, in association with other Renderoc mortars

Advantages

- **Cost effective** - no independent primer necessary
- **Time saving** - curing not necessary
- **High performance** - excellent bond to the substrate

Description

Renderoc FC is supplied as a ready to use blend of dry powders which requires only the site addition of clean water to produce a highly consistent cementitious mortar.

Renderoc FC exhibits excellent thermal compatibility with concrete, and is fully compatible with other Renderoc*[†] mortars



Above : Typical Application of Renderoc FC

Specification

The filler for minor surface imperfections (up to 3 mm depth) shall be Renderoc FC-a single component, polymer modified, cementitious mortar. The material shall be capable of use without the need for an independent primer or curing system.

Standard Compliance

Renderoc FC has been approved by the British Board of Agreement, under Certificate No. 98/3461.

Design criteria

Renderoc FC is designed for vertical and overhead use in filling voids up to a depth of 3 mm. It can also be used to render over large areas, from a feather-edge up to 3 mm thickness.

Anti-dusting properties may be imparted upon the mix by the addition of Nitobond SBR*[†] to the gauging water. This will also enhance other performance properties; but should not be viewed as mandatory for every application. However, where subsequent coatings are to be applied, it is important to produce a dust-free surface upon which to apply the coating.

Properties

The following results were obtained at a liquid: powder ratio of 0.25 - 0.28 and temperature of 25°C.

Test Method	Typical result @ 25°C
Coefficient of thermal expansion	: 7 to 12 x 10 ⁻⁶ /°C
Working life Approx. (BS4555)	: 60 mins
Setting time (BS4550 P3)	: ~ 4 hours
Fresh wet density (BS4555)	: Approximately 1,500 -1,600 kg/m ³
Pull off strength (with Nitobond SBR/AR) (ASTM D4541)	: >1.5Mpa

Note: Working life and setting time will vary dependent on ambient and substrate temperatures.

Fosroc Renderoc FC

Instruction for use

Preparation

Clean the surface and remove any dust, unsound material, plaster, oil, paint, grease, corrosion deposits or algae. Roughen the surface to remove any laitance and expose the fine aggregate by light scabbing or grit-blasting.

Oil and grease deposits should be removed by steam cleaning, detergent scrubbing or the use of a proprietary degreaser. The effectiveness of decontamination should then be assessed by a pull-off test.

Renderoc repair mortars require no additional preparation prior to the application of Renderoc FC.

The cleaned areas should be blown clean with oil-free compressed air before continuing. All prepared areas should be thoroughly soaked with clean water immediately prior to the application of Renderoc FC. Any residual surface water should be removed prior to commencement.

Mixing - small quantities

Care should be taken to ensure that Renderoc FC is thoroughly mixed. Small quantities (up to 5 kg) can be mixed using a suitable mixing drum or bucket. Greater quantities should be mixed using a forced-action mixer. Mixing in a suitably sized drum using an approved spiral paddle attached to an approved slow speed (400/500 rpm) heavy-duty drill is an acceptable alternative.

If mixing small quantities by hand, Renderoc FC should be volume-batched. Add 3 volumes of the Renderoc FC powder (loose-filled to excess and struck off level with the top of the measuring container) to one volume of potable water. This should be mixed vigorously until fully homogeneous.

Mixing - large volumes

For larger volumes, place 5.0 to 5.6 litres of cool, potable water into the mixer and, with the machine in operation, then add one full (20 kg) bag of Renderoc FC, and mix continuously for 3 to 5 minutes until fully homogeneous.

Water addition may vary slightly according to both the ambient temperature and the desired consistency of the mix, but it should not exceed 5.6 litres.

For additional anti-dusting, or enhanced performance properties, add 0.9 litres of Nitobond SBR / AR to the gauging water until the desired consistency is achieved.

Note: In all cases Renderoc FC powder must be added to the water.

Application

Apply the mixed Renderoc FC to the prepared substrate, up to 3 mm thickness, by steel trowel. It should be applied with minimal working and be allowed to partly set before finally troweling to a smooth finish.

If a very smooth finish is required, a small amount of water may be flicked on to the surface of the Renderoc FC with a paint brush prior to final troweling.

Do not proceed with the application when rainfall is imminent unless in a sheltered or protected situation.

Finishing

Renderoc FC is finished by striking off with a straight edge and closing with a steel or plastic float. Note that water can be drawn to the surface if 'overworking' with the float occurs, and an unsightly finish may result.

Damp sponges or plastic floats may be used to achieve a desired surface texture, but care should again be taken not to overwork the surface.

Curing

Curing is not generally required. However, under extreme conditions - high temperatures and drying winds - it may be prudent to use Nitobond AR*† as a curing agent.

Nitobond AR does **not** require mechanical removal prior to over-coating.

Cleaning

Renderoc FC should be removed from tools, equipment and mixers with clean water immediately after use. Cured material can only be removed by mechanical means.

Fosroc Renderoc FC

Limitations

- If applying decorative or protective coating, it is recommended to use Nitobond SBR / AR with Renderoc FC to impart improved anti-dusting properties as described above
- Renderoc FC should not be used when the temperature is below 5°C and falling.
- Do not proceed with the application when rainfall is imminent unless in a sheltered or protected situation.
- The product should not be exposed to moving water during application or prior to initial set.
- If any doubts arise concerning temperature or substrate conditions, consult the local Fosroc office.

High temperature working

It is suggested that, for temperatures above 35°C, the following guidelines are adopted as good working practice:

- Store unmixed materials in a cool (preferably temperature controlled) environment, avoiding exposure to direct sunlight.
- Keep equipment cool, arranging shade protection if necessary. It is especially important to keep cool those surfaces of the equipment which will come into direct contact with the material itself.
- Try to avoid application during the hottest times of the day, and in direct sunlight.
- Make sufficient material, plant and labour available to ensure that application is a continuous process.

Technical support

Fosroc offers a comprehensive technical support service to specifiers, end users and contractors. It is also able to offer on-site technical assistance, an AutoCAD facility and dedicated specification assistance in locations all over the world.

Estimating

Supply

Renderoc FC : 20kg bags

Nitobond SBR : 25 and 200 litres drums

Nitobond AR : 1 and 5 litres drums

Coverage

Renderoc FC : 15L(5.2m² @3mm thick/20kg bag)

Nitobond AR : 6 to 8 m² per litre

Note: Actual coverage of Renderoc FC will be wholly dependent upon the general substrate condition. It is recommended, therefore, that site trials over a typical area are carried out to determine actual usage.

Storage

Shelf life

All products have a shelf life of 12 months if kept in a dry store in the original, unopened bags or packs @ 25°C.

Storage conditions

Store in dry conditions in the original, unopened bags or packs. If stored at high temperatures and/or high humidity conditions the shelf life may be considerably reduced to 4 to 6 months.

Precautions

Health and safety

Renderoc FC contains cement powders which, when mixed or become damp, release alkalis which can be harmful to the skin. Nitobond AR and Nitobond SBR are slightly alkaline.

During use, avoid inhalation of dust and contact with skin and eyes. Wear suitable protective clothing, gloves, eye protection and respiratory protective equipment.

The use of barrier creams can provide additional skin protection. In case of contact with skin, rinse with plenty of clean water, then cleanse with soap and water. In case of contact with eyes, rinse immediately with plenty of clean water and seek medical advice. If swallowed, seek medical attention immediately - **do not** induce vomiting.

For further information, refer to the appropriate Product Material Safety Data Sheet.

Fosroc Renderoc FC

Fire

Renderoc FC, Nitobond AR and Nitobond SBR are all non-flammable products.

Additional information

Fosroc manufactures a wide range of complementary product which include:

- Waterproofing membranes & waterstop
- Joint sealants & filler boards
- Cementitious & epoxy grouts
- Specialised flooring materials

Fosroc additionally offers a comprehensive package of products specifically designed for the repair and refurbishment of damaged concrete. Fosroc's 'Systematic Approach' to concrete repair features the following:

- hand-placed repair mortars
- spray grade repair mortars
- fluid micro-concretes
- chemically resistant epoxy mortars
- anti-carbonation/anti-chloride protective coatings
- chemical and abrasion resistant coatings

For further information on any of the above, please consult your local Fosroc office– as below,

* Denotes the trademark of Fosroc International Limited
† See separate data sheet



Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Services, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification of information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it.

Fosroc International

Malaysia

Fosroc Sdn. Bhd

Tel : +60 3 5102 5660

Enquiry: malaysia@fosroc.com

Singapore

Fosroc Singapore

Tel: +65 6665 3828

Enquiry: singapore@fosroc.com

Thailand

Fosroc Thailand

Tel : +66 2 136 9898

Enquiry: thailand@fosroc.com

Vietnam

Fosroc Vietnam

Tel : +82 222 3765 971

Enquiry: vietnam@fosroc.com

Rest of Southeast Asia

Fosroc Construction Chemicals Pte Ltd

Tel : +65 6665 3828

Enquiry: FGTAsia@fosroc.com

www.fosroc.com